

End Uses

SPX extensible high performance unbleached kraft paper has superior Tensile Energy Absorption (TEA) and balanced strength characteristics in both the machine and cross direction.

Even stronger than SPK, multiwall shipping sacks made from SPX use less paper in demanding applications for a variety of products such as cement and other construction materials. Typically used in pasted valve sacks.

Fibre Source

SPX is manufactured with a blend of virgin fibre from Black Spruce and Jack Pine. These northern boreal slow growing woods have exceptionally high strength potential. Canadian Kraft Paper (CKP) fibre is harvested and replanted in accordance with sustainable forest management practices under CSA, PEFC, and ISO 14001 environmental quality control standards.

Quality Systems

SPX quality is controlled with a comprehensive management system registered to ISO 9001 and incorporating elements of environmental (ISO 14001) and employee health and safety (OHAS 18001) management systems. CKP manufactures kraft papers in compliance with FDA as per 21 CFR 176.170 and 176.180, CONEG heavy metals and toxics, German recommendation XXXVI, 94/62/EEC certifications and is Kosher certified. This paper meets the requirements for packaging recoverable by composting and degradation ISO 17088 (2008) and EN 13432 2000. Certificates of compliance to all applicable regulatory requirements will be supplied upon request.

Typical Values SI

Properties	Units						Test Method	
Basis Weight	gsm		70	80	85	90	95	ISO 536
Tensile	kN/m	MD	6.2	7.1	7.6	8.0	8.4	ISO 1924-3
		CD	4.5	5.1	5.4	5.8	6.0	
Tensile Index	Nm/g	MD	88	88	88	88	88	ISO 1924-3
		CD	64	64	64	64	64	
Stretch	%	MD	6.8	6.8	6.8	6.8	6.8	ISO 1924-3
		CD	8.9	8.9	8.9	8.9	8.9	
TEA	J/m ²	MD	220	250	265	280	295	ISO 1924-3
		CD	245	275	290	310	320	
TEA Index	J/g	MD	3.1	3.1	3.1	3.1	3.1	ISO 1924-3
		CD	3.4	3.4	3.4	3.4	3.4	
Tear	mN	MD	850	980	1065	1125	1200	ISO 1974
		CD	920	1060	1150	1225	1325	
Air Resistance	Sec/100cc		15	15	15	15	15	ISO 5636-5
Cobb	g/m ² /min		30	30	30	30	30	ISO 535
Moisture	%		7.5	7.5	7.5	7.5	7.5	ISO 287

Product specifications in effect as of July 1, 2019

MD – Machine Direction CD – Cross Direction

Paper Test Conditions: Temperature = 23+/-1°C, Relative Humidity = 50+/-2%

Marketed by



Premium 1 Papers 473 West Ave · Kelowna, BC · V1Y 4Z3
Tel: 250.870.5250 Toll Free: 1.866.611.5268
www.premium1papers.com



End Uses

SPX extensible high performance unbleached kraft paper has superior Tensile Energy Absorption (TEA) and balanced strength characteristics in both the machine and cross direction.

Even stronger than SPK, multiwall shipping sacks made from SPX use less paper in demanding applications for a variety of products such as cement and other construction materials. Typically used in pasted valve sacks.

Fibre Source

SPX is manufactured with a blend of virgin fibre from Black Spruce and Jack Pine. These northern boreal slow growing woods have exceptionally high strength potential. Canadian Kraft Paper (CKP) fibre is harvested and replanted in accordance with sustainable forest management practices under CSA, PEFC, and ISO 14001 environmental quality control standards.

Quality Systems

SPX quality is controlled with a comprehensive management system registered to ISO 9001 and incorporating elements of environmental (ISO 14001) and employee health and safety (OHAS 18001) management systems. CKP manufactures kraft papers in compliance with FDA as per 21 CFR 176.170 and 176.180, CONEG heavy metals and toxics, German recommendation XXXVI, 94/62/EEC certifications and is Kosher certified. This paper meets the requirements for packaging recoverable by composting and degradation ISO 17088 (2008) and EN 13432 2000. Certificates of compliance to all applicable regulatory requirements will be supplied upon request.

Typical Values Imperial

Properties	Units						Test Method	
Basis Weight	lbs/3000ft ²		43	50	52	55	58	ISO 536
Tensile	lbs/in	MD	35.4	40.5	43.4	45.7	48.0	ISO 1924-3
		CD	25.7	29.1	30.8	33.1	34.3	
Tensile Index	Nm/g	MD	88	88	88	88	88	ISO 1924-3
		CD	64	64	64	64	64	
Stretch	%	MD	6.8	6.8	6.8	6.8	6.8	ISO 1924-3
		CD	8.9	8.9	8.9	8.9	8.9	
TEA	ft lb/ft ²	MD	15.1	17.1	18.2	19.2	20.2	ISO 1924-3
		CD	16.8	18.8	19.9	21.2	21.9	
TEA Index	J/g	MD	3.1	3.1	3.1	3.1	3.1	ISO 1924-3
		CD	3.4	3.4	3.4	3.4	3.4	
Tear	g	MD	85	100	110	115	120	ISO 1974
		CD	95	105	115	125	135	
Air Resistance	sec/100cc		15	15	15	15	15	ISO 5636-5
Cobb	g/m ² /min		30	30	30	30	30	ISO 535
Moisture	%		7.5	7.5	7.5	7.5	7.5	ISO 287

Product specifications in effect as of July 1, 2019

MD – Machine Direction CD – Cross Direction

Paper Test Conditions: Temperature = 73.4±1.8°F, Relative Humidity = 50%±2%

Marketed by



Premium 1 Papers 473 West Ave · Kelowna, BC · V1Y 4Z3
Tel: 250.870.5250 Toll Free: 1.866.611.5268
www.premium1papers.com

