

# SPX® - Velocity

## Technical Data Sheet



### End Uses

SPX-Velocity extensible high porous sack kraft paper is characterized by high strength in both the machine and cross direction with a high degree of air permeability.

The high porous paper allows for quick filling of the product without perforations, a cleaner dust-free environment and a cost effective packaging solutions.

### Fibre Source

CKP paper is manufactured using unbleached kraft pulp and consists of 100% Northern Canadian virgin fibre. The slow growing softwood forests provide long fibre that gives our paper its superior strength. The fibre is harvested and replanted in accordance with sustainable forest management practices. CKP paper is fully biodegradable and is an eco-friendly packaging choice.

### Approvals

CKP paper is produced in compliance with FDA CONEG, and BfR food packaging requirements.

### Certification

Production of CKP paper is certified in accordance to ISO 9001 quality management system, KSA Kosher, ISEGA & SGS Food Contact. CKP Forest Management system is certified to CSA, PEFC Chain of Custody & ISO 14001 environment management.

### Typical Values SI

| Properties     | Units                 |    |     |      |      | Test Method |            |
|----------------|-----------------------|----|-----|------|------|-------------|------------|
| Basis Weight   | gsm                   |    | 70  | 80   | 90   | 98          | ISO 536    |
| Tensile        | kN/m                  | MD | 5.8 | 6.6  | 7.4  | 8.0         | ISO 1924-3 |
|                |                       | CD | 4.2 | 4.8  | 5.4  | 6.0         |            |
| Tensile Index  | Nm/g                  | MD | 82  | 82   | 82   | 82          | ISO 1924-3 |
|                |                       | CD | 60  | 60   | 60   | 60          |            |
| Stretch        | %                     | MD | 6.8 | 6.8  | 6.8  | 6.8         | ISO 1924-3 |
|                |                       | CD | 8.9 | 8.9  | 8.9  | 8.9         |            |
| TEA            | J/m <sup>2</sup>      | MD | 210 | 240  | 270  | 290         | ISO 1924-3 |
|                |                       | CD | 230 | 260  | 290  | 310         |            |
| TEA Index      | J/g                   | MD | 3.0 | 3.0  | 3.0  | 3.0         | ISO 1924-3 |
|                |                       | CD | 3.3 | 3.3  | 3.2  | 3.2         |            |
| Tear           | mN                    | MD | 880 | 1000 | 1130 | 1270        | ISO 1974   |
|                |                       | CD | 945 | 1100 | 1230 | 1350        |            |
| Air Resistance | Sec/100cc             |    | 5   | 5    | 5    | 5           | ISO 5636-5 |
| Cobb           | g/m <sup>2</sup> /min |    | 30  | 30   | 30   | 30          | ISO 535    |
| Moisture       | %                     |    | 7.5 | 7.5  | 7.5  | 7.5         | ISO 287    |

Product specifications in effect as of July 1, 2020

MD – Machine Direction CD – Cross Direction

Paper Test Conditions: Temperature = 23+/-1°C, Relative Humidity = 50%+/-2%

Marketed by



Premium 1 Papers 473 West Ave · Kelowna, BC · V1Y 4Z3  
Tel: 250.870.5250 Toll Free: 1.866.611.5268  
www.premium1papers.com



# SPX® - Velocity

## Technical Data Sheet



### End Uses

SPX-Velocity extensible high porous sack kraft paper is characterized by high strength in both the machine and cross direction with a high degree of air permeability.

The high porous paper allows for quick filling of the product without perforations, a cleaner dust-free environment and a cost effective packaging solutions.

### Fibre Source

CKP paper is manufactured using unbleached kraft pulp and consists of 100% Northern Canadian virgin fibre. The slow growing softwood forests provide long fibre that gives our paper its superior strength. The fibre is harvested and replanted in accordance with sustainable forest management practices. CKP paper is fully biodegradable and is an eco-friendly packaging choice.

### Approvals

CKP paper is produced in compliance with FDA CONEG, and BfR food packaging requirements.

### Certification

Production of CKP paper is certified in accordance to ISO 9001 quality management system, KSA Kosher, ISEGA & SGS Food Contact. CKP Forest Management system is certified to CSA, PEFC Chain of Custody & ISO 14001 environment management.

### Typical Values Imperial

| Properties     | Units                   |    |      |      |      | Test Method |            |
|----------------|-------------------------|----|------|------|------|-------------|------------|
| Basis Weight   | lbs/3000ft <sup>2</sup> |    | 43   | 50   | 55   | 60          | ISO 536    |
| Tensile        | lbs/in                  | MD | 33.1 | 37.7 | 42.3 | 45.7        | ISO 1924-3 |
|                |                         | CD | 24.0 | 27.4 | 30.8 | 34.3        |            |
| Tensile Index  | Nm/g                    | MD | 82   | 82   | 82   | 82          | ISO 1924-3 |
|                |                         | CD | 60   | 60   | 60   | 60          |            |
| Stretch        | %                       | MD | 6.8  | 6.8  | 6.8  | 6.8         | ISO 1924-3 |
|                |                         | CD | 8.9  | 8.9  | 8.9  | 8.9         |            |
| TEA            | ft lb/ft <sup>2</sup>   | MD | 14.4 | 16.4 | 18.5 | 19.9        | ISO 1924-3 |
|                |                         | CD | 15.8 | 17.8 | 19.9 | 21.2        |            |
| TEA Index      | J/g                     | MD | 3.0  | 3.0  | 3.0  | 3.0         | ISO 1924-3 |
|                |                         | CD | 3.3  | 3.3  | 3.2  | 3.2         |            |
| Tear           | g                       | MD | 90   | 105  | 115  | 130         | ISO 1974   |
|                |                         | CD | 95   | 110  | 125  | 140         |            |
| Air Resistance | sec/100cc               |    | 5    | 5    | 5    | 5           | ISO 5636-5 |
| Cobb           | g/m <sup>2</sup> /min   |    | 30   | 30   | 30   | 30          | ISO 535    |
| Moisture       | %                       |    | 7.5  | 7.5  | 7.5  | 7.5         | ISO 287    |

Product specifications in effect as of July 1, 2020

MD – Machine Direction CD – Cross Direction

Paper Test Conditions: Temperature = 73.4+/-1.8°F, Relative Humidity = 50%+/-2%

Marketed by



Premium 1 Papers 473 West Ave · Kelowna, BC · V1Y 4Z3  
Tel: 250.870.5250 Toll Free: 1.866.611.5268  
www.premium1papers.com

