

SPX-Velocity®

Technical Data Sheet



End Uses

SPX-Velocity® extensible high porous sack kraft paper is characterized by high strength in both the machine and cross direction with a high degree of air permeability.

The high porous paper allows for quick filling of the product without perforations, a cleaner dust-free environment and cost effective packaging solutions.

Fibre Source

CKP paper is manufactured using unbleached kraft pulp and consists of 100% Northern Canadian virgin fibre. The slow growing softwood forests provide long fibre that gives our paper its superior strength. The fibre is harvested and replanted in accordance with sustainable forest management practices. CKP paper is fully biodegradable and is an eco-friendly packaging choice.

Approvals

CKP paper is produced in compliance with FDA CONEG, and BfR food packaging requirements.

Certification

Production of CKP paper is certified in accordance to ISO 9001 quality management system and ISEGA Food Contact. CKP Forest Management system is certified to CSA, PEFC Chain of Custody & ISO 14001 environment management.

Typical Values SI

Properties	Units					Test Method	
Basis Weight	gsm		70	80	90	98	ISO 536
Tensile	kN/m	MD	5.8	6.6	7.4	8.0	ISO 1924-3
		CD	4.2	4.8	5.4	6.0	
Tensile Index	Nm/g	MD	82	82	82	82	ISO 1924-3
		CD	60	60	60	60	
Stretch	%	MD	6.8	6.8	6.8	6.8	ISO 1924-3
		CD	8.9	8.9	8.9	8.9	
TEA	J/m ²	MD	210	240	270	290	ISO 1924-3
		CD	230	260	290	310	
TEA Index	J/g	MD	3.0	3.0	3.0	3.0	ISO 1924-3
		CD	3.3	3.3	3.2	3.2	
Tear	mN	MD	900	1000	1150	1220	ISO 1974
		CD	945	1100	1250	1350	
Air Resistance	sec/100cc		5	5	5	5	ISO 5636-5
Cobb	g/m ² /min		30	30	30	30	ISO 535
Moisture	%		7.5	7.5	7.5	7.5	ISO 287

In effect from July 1, 2022

MD – Machine Direction CD – Cross Direction

Paper Test Conditions: Temperature = 23+/-1°C, Relative Humidity = 50%+/-2%



SPX-Velocity®

Technical Data Sheet



End Uses

SPX-Velocity® extensible high porous sack kraft paper is characterized by high strength in both the machine and cross direction with a high degree of air permeability.

The high porous paper allows for quick filling of the product without perforations, a cleaner dust-free environment and cost effective packaging solutions.

Fibre Source

CKP paper is manufactured using unbleached kraft pulp and consists of 100% Northern Canadian virgin fibre. The slow growing softwood forests provide long fibre that gives our paper its superior strength. The fibre is harvested and replanted in accordance with sustainable forest management practices. CKP paper is fully biodegradable and is an eco-friendly packaging choice.

Approvals

CKP paper is produced in compliance with FDA CONEG, and BfR food packaging requirements.

Certification

Production of CKP paper is certified in accordance to ISO 9001 quality management system and ISEGA Food Contact. CKP Forest Management system is certified to CSA, PEFC Chain of Custody & ISO 14001 environment management.

Typical Values Imperial

Properties	Units					Test Method	
Basis Weight	lbs/3000ft ²		43	50	55	60	ISO 536
Tensile	lbs/in	MD	33.1	37.7	42.3	45.7	ISO 1924-3
		CD	24.0	27.4	30.8	34.3	
Tensile Index	Nm/g	MD	82	82	82	82	ISO 1924-3
		CD	60	60	60	60	
Stretch	%	MD	6.8	6.8	6.8	6.8	ISO 1924-3
		CD	8.9	8.9	8.9	8.9	
TEA	ft lb/ft ²	MD	14.4	16.4	18.5	19.9	ISO 1924-3
		CD	15.8	17.8	19.9	21.2	
TEA Index	J/g	MD	3.0	3.0	3.0	3.0	ISO 1924-3
		CD	3.3	3.3	3.2	3.2	
Tear	g	MD	90	105	115	125	ISO 1974
		CD	95	110	125	140	
Air Resistance	sec/100cc		5	5	5	5	ISO 5636-5
Cobb	g/m ² /min		30	30	30	30	ISO 535
Moisture	%		7.5	7.5	7.5	7.5	ISO 287

In effect from July 1, 2022

MD – Machine Direction CD – Cross Direction

Paper Test Conditions: Temperature = 73.4+/-1.8°F, Relative Humidity = 50%+/-2%

